













ETALON
PRODUCTS FOR REAL CRAFTSMEN

440VAF 4:1 2K ACRYLIC PRIMER

ET440VAF-10/B 1L, black
ET440VAF-10/G 1L, light grey
ET440VAF-30/G 3L, light grey

	Product	2K acrylic primer, fast drying and easy sanding.
	Substrates	Steel old paint, body filler, OEM primers and fiberglass.
	Surface Preparation	In case of application over body filler and putties dry sand with P180-P240. Clean and degrease thoroughly. Use tack cloth for heavy dust.
	Application Conditions	18-22°C
	Mixing	By volume 4:1 with Etalon ET995 hardener fast and extra fast. By weight: 1000gr (A) - 150gr (B)
	Dilution	Acrylic reducer (thinner) 10%
	Pot Life	60 min
	Application Viscosity	15-19 sec
	Spraying Equipment	Gravity spray gun 1.6-1.8mm
	Number of layers	2 coats
	Flash off	8-10min
	Coating Thickness	50-80µm
	Drying	3-5 hours at 20°C 30 min at 60°C
	Sanding	Dry sanding with P400 for solid colours and P500 for metallics
	VOC	2004/42/IIIB(c)(540)370 g/l
	Shelf life	12 months