



## 98PL 2:1 SR CLEARCOAT

ET98PL-SR011L ET98PL-SR055L

Product	2K scratch resistant acrylic clearcoat. High-gloss and excellent durability
Substrates	Apply on top of fully dry solvent or water-born base coats.
Surface Preparation	The use of tack cloth is recommended prior application.
Application Conditions	18-22°C
Mixing	2:1 by volume with Etalon ET995 ECO hardener normal, fast, exfast.
Dilution	No dilution required
Pot Life	2-3 hours at 20°C
Application Viscosity	14-15sec at 20°C Ford cup 4
Spraying Equipment	Gravity feed gun - 1.3mm
Number of layers	2 coats
Flash off	5-10 min
Coating Thickness	45-50 microns
Drying	Touch Dry: 5-6 hours at 20°C Fully Dry: 16-18 hours at 20°C Sandable after approx. 30min. at 60°C
Drying with IR lamps	14-15min
voc	525 g/l
Shelf life	12 months

Technical Data Sheet etalon-refinish.com