



5900PP PLASTIC BODY FILLER

ET5900PP, 1kg black

	Product	2K elastic polyester putty developed for the applications on coatable plastic parts, like bumpers.
	Substrates	Flexible thermoplastics used in cars manufacturing.
	Surface Preparation	Clean flatten and degrease prior application.
	Application Conditions	From +10°C.
P	Mixing	2-3% with hardener
	Number of layers	1-2 layers
	Drying	20-30min at 20°C.
	Drying with IR lamps	Approximately 10min
R	Sanding	Dry sanding only with P120-P240.
	Shelf life	12 months