

Technical Information

35 Line



35- Basecoat

Basecoat for solid color, metallic and pearl coatings

- High solid and pigment content – good hiding power
- Low material consumption
- Short flash-off time

Application

	Mixing Ratio	100 % by volume	
	2:1	50 % by volume	60-10, -20, -30, -40
	Spray viscosity at 20°C		DIN 4: 18-22 s
	Potlife at 20°C		48 h
	HVLP spray gun		
	Nozzle size		1.3 mm
	Application pressure		2 bar
	Nozzle pressure		0.7 bar
	Compliant gravity-feed spray gun		
	Nozzle Size		1.3-1.4 mm
	Application Pressure		2 bar
	Number of spray coats	2 (spray to cover) + ½ to match the effect	
	Film thickness	15-20 µm	
	Flash off at 20°C	10 min until mat	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.